

AQUAPEL 758

Water Resisting Admixture

PRODUCT DESCRIPTION

Aquapel 758 is a specially formulated water resisting admixture developed to reduce the permeability of concrete. **Aquapel 758** is particularly beneficial in dry or semi-dry concrete and masonry mortars.

APPLICATIONS

Aquapel 758 is used to improve the waterproof properties of concrete and mortar by forming a permanent hydrophobic layer at the air-concrete interface.

BENEFITS

- Reduced shrinkage.
- Reduced permeability.
- Increased water tightness.
- Reduced efflorescence.

PROPERTIES

Nature:	Liquid
Appearance:	Clear Amber
Specific Gravity: (20°C)	1.00 g/cm ³
pH:	>11.5
Chloride Content:	< 0.10
Alkali Content (Na ₂ O):	< 4.00

ADDITION RATES

Dosage rates vary dependant on mix design, process, aggregate type and the desired effect but typically:

500mls—3000mls per 100kg cement

(0.50% - 3.00% by weight of cement)

The correct dosage for the material package used should be determined by laboratory trials, please contact the OSCRETE technical department for further advice.

STANDARDS

Aquapel 758 conforms to the requirements of BS EN 934-2 and is produced in accordance with the ISO 9001 Quality Management Standard and the ISO 14001 Environmental Management Standard.



AQUAPEL 758

Water Resisting Admixture

COMPATIBILITY

Aquapel 758 is compatible with all types of EN 197 cement systems.

Aquapel 758 should not be premixed with other admixtures and should be batched separately.

STORAGE

Aquapel 758 should be protected from extreme temperature, frost and direct sunlight, the product has a minimum shelf life of 12 months.

HANDLING

Please refer to the **Aquapel 758** material safety data sheet but in line with normal handling procedures, personal protective equipment should be worn.

PACKAGING

1000 litre IBC's and bulk deliveries.

NOTES

Aquapel 758 should be added with the water or at the end of the mixing process and not directly onto the cement. A mixing time of at least 30 seconds is recommended after the addition of the admixture.

If frozen **Aquapel 758** may be used after thawing, slowly at room temperature followed by intensive mixing.

Aquapel 758 is designed for use in dry/semi-dry concrete and masonry mortar, if used in wet concrete over 50mm slump increases in air-entrainment will be observed.

Please consult the OSCRETE technical department for advice on admixture selection.

OSCRETE UK Limited
Rutland Street
Bradford
West Yorkshire
BD4 7EA
United Kingdom

Telephone: +44 (0)1274 086299
E-mail: technical@oscrete.com
Website: www.oscrete.com

PDS 0804 Rev 06 02/01/2024

Disclaimer

The physical properties quoted are typical, and should not be taken as a specification. The information supplied in our literature is based on data and experience and is given in good faith. Our policy is one of continuous research and development and we reserve the right to update this information at any time; customers should therefore ensure they have the latest issue. Whilst we guarantee the consistent high quality of our products, we have no control over the circumstances in which our materials are used, site conditions or the execution of the work and are therefore unable to accept any liability for any loss or damage which may arise as a result thereof. Materials are supplied in accordance with our standard conditions of sale.

